



**NATIONAL TESTING STANDARDS INC.**  
RESEARCH AND TESTING LABORATORIES

Report No. 30316

June 7, 2010

Client: Jensen Swing Products, Inc.  
9327 Wheatlands Rd.  
Santee, CA 92071

Reference: Charvet Vecchio  
Purchase Order No. Verbal

Subject: Load Strength of Full Bucket Seat.

Sample Description:

One black colored full bucket style swing seat was submitted by the Client and identified as S100.

Request:

Determine the load strength of each hanger in the submitted swing seat and the total load of the seat.

Method:

The load strength of each hanger in the submitted full bucket seat was determined using an CRE tensile testing machine running at a jaw separation rate of 0.1 inch per minute.

Results:

<u>Hanger No.</u>	<u>Load Strength (lbs.f.)</u>
1	2940
2	3030
total*	5880

\* two times the lowest measurement

NATIONAL TESTING STANDARDS

by Lewis F. West

020