

TEST REPORT

Report No. : HL60523/2020
 Page : 1 of 2
 Date : JUL. 07, 2020

DE LAI PLASTIC CO., LTD.

NO. 2, LN. 96, XINGXONG RD., XIANXI TOWNSHIP, CHANGHUA COUNTY 507, TAIWAN

The following merchandise was submitted and identified by the applicant as:

Product Description: TRIANGULAR ALUMINUM TRAPEZE RING-PLASTISOL YELLOW
Style/Item No.: A185Y
Country of Origin: TAIWAN

We have tested the submitted sample as requested and the following results were obtained:

Test Requested: Pulling test

Test Method:

1. Secure the sample on the testing machine. (See photo B)
2. Apply an increasing upward force to the sample until it is damaged or up to 4,900 kgf.
3. Record the max. force and any findings.
4. Testing Machine: INSTRON 5581, Rate: 10 mm/min.

Test Result:


| Sample | Max. force (kgf) | Remark |
|---|------------------|---|
| TRIANGULAR ALUMINUM TRAPEZE RING-PLASTISOL YELLOW | 1,437 | The sample was damaged after testing. (Photo C) |

Date of Receipt: Jun. 30, 2020

Testing Period: Jun. 30, 2020 ~ Jul. 07, 2020

Note: The content of this report is invalid if it is not presented as the entire report.

Signed for and on behalf of
 SGS Taiwan Ltd.



Sturm Su
 Asst. Manager



TEST REPORT

Report No. : HL60523/2020

Page : 2 of 2

– Picture(s) –



Photo A: Appearance of the sample



Photo B: Test setup



Photo C: After testing

---End of Report---